

Type	Thermocouple Material	Polarity	Operating Temperature Range
K	Chromel Alumel	Positive Negative	-184 to 1260 C
C	Tungsten 5% Rhenium Tungsten 26% Rhenium	Positive Negative	0 to 2760 C
E	Chromel Constantan	Positive Negative	-184 to 900 C
J	Iron Constantan	Positive Negative	0 to 750 C
T	Copper Constantan	Positive Negative	-184 to 400 C
N	NI-CR-SI NI-SI-MG	Positive Negative	-270 to 1300 C
R	Platinum 13% Phodium Platinum	Positive Negative	0 to 1540 C
S	Platinum 10% Phodium Platinum	Positive Negative	0 to 1540 C

vaqtec

vacuum technology & components

Thermocouple table

Not scale drawing

Sheet 1 of 1

Date: 10/02/2011

Revision: 0.0

Dimensions: IN (mm)

Number:

Property and confidential

The information contained in this drawing is the sole property of Vaqtec Srl. Any reproduction in part or as a whole without the written permission of Vaqtec Srl is prohibited.